

Tel: +27 12 803 8595
Fax: +27 12 803 8462
Customer care line: 086 1554 321
e-mail: timberlife@icon.co.za
Website: www.timberlife.co.za

TIMBERLIFE (PTY) LTD
REG No 2000/017132/07



TimberLife

PO Box 73117, Lynnwood Ridge, 0040
31 Axle Street
Silverton Ext 52
Pretoria, South Africa

PRODUCT DATA SHEET

Bipro ST

Product Name:	BIPRO ST								
Product Type:	COMBINED ANTI-SAPSTAIN/MOULD AND ANTI-BORER TREATMENT FOR FRESHLY CUT/SAWN TIMBER								
Description:	<p>BIPRO ST is a water-dispersible liquid concentrate that contains four specifically blended fungicidal and insecticidal active ingredients to provide a wide-spectrum protection against sapstain fungi and mould growth as well as wood borer attack on green (wet) sawn and round timbers.</p> <p>For maximum effect, BIPRO ST should be applied to all timber surfaces as soon as possible after processing and preferably within 12 hours after cutting, debarking and/or sawing.</p>								
Active Ingredients:	Sodium borates, organosulphur compound, tetrachlorophthalonitrile and synthetic pyrethroid								
Physical Characteristics:	<table><tr><td>Appearance</td><td>- Yellowish-white liquid</td></tr><tr><td>Solubility</td><td>- Dispersible in water</td></tr><tr><td>Density @ 20°C</td><td>- ± 1,1 kg/l</td></tr><tr><td>pH</td><td>- ± 6,0</td></tr></table>	Appearance	- Yellowish-white liquid	Solubility	- Dispersible in water	Density @ 20°C	- ± 1,1 kg/l	pH	- ± 6,0
Appearance	- Yellowish-white liquid								
Solubility	- Dispersible in water								
Density @ 20°C	- ± 1,1 kg/l								
pH	- ± 6,0								
Use Restriction:	Only to be used and applied in accordance with label warnings, precautions and direction for use. Never apply product while it is raining.								
Application:	This product can be applied to timber by brush, dip or spray methods. BIPRO ST is supplied as a 249g/l active ingredient concentrate, minimum.								
Application Rate:	± 300ml per m ² for sawn timber and ± 100ml per m ² for round timber.								
Dilution Rates:	<p><u>Sawn timber:</u> 1 part BIPRO ST concentrate to 19; 13 or 10 parts water, depending on timber thickness.</p> <p><u>Round timber:</u> 1 part BIPRO ST concentrate to 7 parts water.</p>								
Storage:	Storage temperatures should not exceed 40 - 50°C. Product may require stirring prior to use to ensure uniformity.								
Packaging:	25l and 200l nett drums								
Note:	Handle with care (Observe label instructions and consult the Materials Safety Data Sheet for more details)								