

Tel: +27 12 803 8595
Fax: +27 12 803 8462
Customer care line: 086 1554 321
e-mail: timberlife@icon.co.za
Website: www.timberlife.co.za

TIMBERLIFE (PTY) LTD
REG No 2000/017132/07



TimberLife

PO Box 73117, Lynnwood Ridge, 0040
31 Axle Street
Silverton Ext 52
Pretoria, South Africa

PRODUCT DATA SHEET

Blupro ST

Product Name:	BLUPRO ST								
Product Type:	ANTI-SAPSTAIN / MOULD TREATMENT FOR FRESHLY CUT/SAWN TIMBER								
Description:	<p>BLUPRO ST is a water-dispersible liquid concentrate containing three specially blended active ingredients of high fungicidal activity and persistence on treated wood. BLUPRO ST is formulated specifically to protect green pine timbers, freshly sawn and/or in its round form, from infection by fungi that causes sapstain, mould growth and incipient decay.</p> <p>For maximum effect, BLUPRO ST should be applied to all timber surfaces as soon as possible after processing and preferably within 12 hours after cutting, debarking and/or sawing.</p>								
Active Ingredients:	Sodium borates, organosulphur compound and tetrachlorophthalonitrile								
Physical Characteristics:	<table><tr><td>Appearance</td><td>- Yellowish-white liquid</td></tr><tr><td>Solubility</td><td>- Dispersible in water</td></tr><tr><td>Density @ 20°C</td><td>- ± 1,10 kg/ℓ</td></tr><tr><td>pH</td><td>- ± 6,0</td></tr></table>	Appearance	- Yellowish-white liquid	Solubility	- Dispersible in water	Density @ 20°C	- ± 1,10 kg/ℓ	pH	- ± 6,0
Appearance	- Yellowish-white liquid								
Solubility	- Dispersible in water								
Density @ 20°C	- ± 1,10 kg/ℓ								
pH	- ± 6,0								
Use Restriction:	Only to be used and applied in accordance with label warnings, precautions and directions for use. Never apply product while it is raining								
Application:	This product can be applied to timber by brush, dip or spray methods. BLUPRO ST is supplied as a 250g/ℓ active ingredient concentrate, minimum.								
Application Rate:	± 0,3ℓ per m ² for sawn timber and ± 0,1 ℓ per m ² for round timber								
Dilution Rates:	<p><u>Sawn timber:</u> 1 part BLUPRO ST concentrate to 17; 12 or 10 parts water, depending on timber thickness.</p> <p><u>Round timber:</u> 1part BLUPRO ST concentrate to 8 parts water.</p>								
Storage:	Storage temperatures should not exceed 35 - 40°C. Product may require stirring prior to use to ensure uniformity.								
Packaging:	25ℓ and 200ℓ nett drums								
Note:	Handle with care (Observe label instructions)								